

IMPACT NATURAL

Recycled paper produced of 100 % recovered fibre.

Manufactured without optical brightening agents and chlorine bleaching, high whiteness thanks to a special converting process for recovered fibre. Product exhibits high opacity and good sheet formation as well as maximum ageing resistance. Excellent usability given on all types of processing machinery for application from envelopes to annual reports. Available for laser and inkjet upon request.

BASIS WEIGHT (g/m ²), ISO 536	70	80	90	100	115	135	150	170	190	250	300
THICKNESS (µm), ISO 534	90	100	113	125	145	165	185	210	235	300	360
OPACITY (%), ISO 2471	≥ 91	≥ 93	≥ 95	≥ 96	≥ 97	≥ 98					
ROUGHNESS BENDTSEN (SS) (ml/min), DIN 53108	160	160	160	160	160	160	160	160	190	160	160
PREPRINT		x	x	x							

February 2019

QUALITÄTSDATEN

- ◆ Weiße CIE ISO 11475: 90 %
- ◆ Weiße ISO 2470: 80 %
- ◆ Volumen: 1,25 cm³/g
- ◆ Cobb 60: ≤30 g/m²
- ◆ Feuchte rel. Offset: 45 %
- ◆ Feuchte rel. Preprint: 35 %

PRODUKTMERKMALE

- ◆ 100 % Altpapier
- ◆ Für Laser und Inkjet
- ◆ Angenehm hohe Weiße
- ◆ Hohe Opazität und Reinheit
- ◆ Beste Laufeigenschaften
- ◆ Alterungsbeständigkeit
DIN 6738: LDK 24-85
- ◆ Basierend auf Bioenergie und
lokaler Beschaffung
- ◆ Integrierte Deinking-Anlage
- ◆ Closed loop; keine Deponierung
- ◆ In Rolle und Format

ZERTIFIKATE

- ◆ ISO 9001
- ◆ ISO 14001
- ◆ DIN 6738



www.blauer-engel.de/uz14a



2044 0053



AT/11/002



The mark of responsible forestry

