

## TECHNICAL DATA SHEET

### Scheda Tecnica

Mod. PG 7.06-01 rev.3 del 18/03/10

<b>Product</b> <b>GLAM SILVER</b>	<b>Weight</b> <b>120 g/m<sup>2</sup></b>
--------------------------------------	---

Characteristic	Internal Method	Standard Reference	Unit of Measure	Side or Direction	Specific Values	Tolerance 2σ
<b>Substance</b>	PO 301	ISO 536	g/m <sup>2</sup>	-	120,0	± 5%
<b>Thickness</b>	PO 303	ISO 534	µm	-	148,0	± 5%
<b>Absolute Humidity</b>	PO 302	ISO 287	%	-	6,0	± 1,0
<b>L&amp;W Stiffness (15°/ 10 mm)</b>	PO 323	ISO 2493	mN	MD	200	>
<b>L&amp;W Stiffness (15°/ 10 mm)</b>	PO 323	ISO 2493	mN	CD	100	>
<b>Roughness Bendtsen</b>	PO 309	ISO 8791-2	ml/min	-	300	± 100

The technical data sheet shall be deemed accepted if not challenged within one month of receipt.

<b>Emission Date</b>	01/02/2020
<b>TDS n°</b>	02AGM
<b>Period of Validity</b>	Until next review
<b>R&amp;S Manager</b>	Renato Burba

Our internal methods are based upon the indicated official methods, but could differ in some details. The above data have been agreed in good faith and tested to the best of our knowledge, but we cannot guarantee the results of further reprocessing that are beyond our control.

We recommend that the Clients, in all cases, evaluate if the characteristics of our paper fit their actual needs and the requirements of the final products.

## TECHNICAL DATA SHEET

### Scheda Tecnica

Mod. PG 7.06-01 rev.3 del 18/03/10

<b>Product</b> <b>GLAM SILVER</b>	<b>Weight</b> <b>290 g/m<sup>2</sup></b>
--------------------------------------	---

Characteristic	Internal Method	Standard Reference	Unit of Measure	Side or Direction	Specific Values	Tolerance 2σ
<b>Substance</b>	PO 301	ISO 536	g/m <sup>2</sup>	-	290,0	± 5%
<b>Thickness</b>	PO 303	ISO 534	µm	-	345,0	± 5%
<b>Absolute Humidity</b>	PO 302	ISO 287	%	-	6,0	± 1,0
<b>L&amp;W Stiffness (15°/ 50 mm)</b>	PO 325	ISO 2493	mN	MD	200	>
<b>L&amp;W Stiffness (15°/ 50 mm)</b>	PO 325	ISO 2493	mN	CD	100	>
<b>Roughness Bendtsen</b>	PO 309	ISO 8791-2	ml/min	-	300	± 100

The technical data sheet shall be deemed accepted if not challenged within one month of receipt.

<b>Emission Date</b>	01/05/2018
<b>TDS n°</b>	02BGM
<b>Period of Validity</b>	Until next review
<b>R&amp;S Manager</b>	Renato Burba

Our internal methods are based upon the indicated official methods, but could differ in some details. The above data have been agreed in good faith and tested to the best of our knowledge, but we cannot guarantee the results of further reprocessing that are beyond our control.

We recommend that the Clients, in all cases, evaluate if the characteristics of our paper fit their actual needs and the requirements of the final products.